

Azul Valverde, portugisisk kalksten.

Technische Daten

Bulk density	2,690 t/m ³
Pressure resistance	143,1 MPa
Druckfestigkeit Frost	130,0 MPa
Abrasion resistance according to Italian standard	2,3
Bending strength	28,6 MPa
Water absorption	0,29 Gew.-%
Porosity	0,47 Vol.-%
Thermische Dehnung	0,49 mm/m/100K